

TECHNICAL DATA SHEET

Office Standard Cut-Size

Physical Parameters

| | REFERENCE | TARGET | TYPICAL | VALUES |
|--------------------------------|-----------------|--------|---------|--------|
| Basis Weight, g/m ² | ISO 536 | 70.0 | 67.2 | 72.8 |
| Thickness, µm | ISO 534 | 101 | 96.0 | 106 |
| Stiffness MD, mN | ISO 2493-1 | | ≥ 90 | |
| Stiffness CD, mN | ISO 2493-1 | | ≥ 30 | |
| Tensile MD, kN/m | ISO 1924-2 | | ≥ 4.5 | |
| Bendtsen Roughness, ml/min | ISO 8791-2 | 230 | 160 | 300 |
| Air Permeability, ml/min | ISO 5636-3 | | | ≤ 1700 |
| Moisture, % | ISO 287 | 4.0 | 3.5 | 4.5 |
| Formation, # | Internal Method | | ≥ 25 | |

Optical Parameters

| | REFERENCE | TARGET | TYPICAL | VALUES |
|-------------------|------------|--------|---------|--------|
| Whiteness, CIE | ISO 11475 | 161 | 158 | 164 |
| Brightness D65, % | ISO 2470-2 | 110 | 107 | 113 |
| Opacity, % | ISO 2471 | 91 | ≥ 89 | |

Approved by:

Technical Department: Eng. Cidália Torre Abreu

sgftp / ftp_sheets FTP-PAP-0424 Rev.: 001 - Data: 202: intmag3c Printed on: 2024/07/19 01:21:52



MANAGEMENT SYSTEMS INFORMATION

- The Navigator Company's papers are made from Elemental Chlorine Free (ECF) bleached kraft pulp;
- The Navigator Company's papers are produced in a neutral/slightly alkaline papermaking process, therefore considered as "acid free" products which meet the requirements of ISO 9706 standard, "Information and documentation – Paper for documents – Requirements for permanence";
- The Navigator Company's laboratories are accredited according to the ISO 17025 standard;
- Quality, Environmental, Health, Safety and Energy Management Systems are certified according to the ISO 9001, ISO 14001, ISO 45001 and ISO 50001 standards;
- The Navigator Company is chain-of-custody certified according to standards FSC-STD-40-004 and FSC-STD-40-005 (NC-COC/CW-014433) and to standard PEFC ST 2002 (APCER-PEFC-COC-070008).